

表 1(续)

牌号	包铝分类	供应状态	试样状态	厚度 ^a /mm	抗拉强度 ^b R_m /MPa	规定非比例 延伸强度 ^b $R_{p0.2}$ /MPa	断后伸长率/%		弯曲 半径 ^d
							A_{50mm}	$A_{5.65}^c$	
不 小 于									
5005	—	H12	H12	>0.20~0.50	125~165	95	2	—	0t
				>0.50~1.50			2	—	0.5t
				>1.50~3.00			4	—	1.0t
				>3.00~6.00			5	—	1.0t
		H14	H14	>0.20~0.50	145~185	120	2	—	0.5t
				>0.50~1.50			2	—	1.0t
				>1.50~3.00			3	—	1.0t
				>3.00~6.00			4	—	2.0t
		H16	H16	>0.20~0.50	165~205	145	1	—	1.0t
				>0.50~1.50			2	—	1.5t
				>1.50~3.00			3	—	2.0t
				>3.00~4.00			3	—	2.5t
		H18	H18	>0.20~0.50	185	165	1	—	1.5t
				>0.50~1.50			2	—	2.5t
				>1.50~3.00			2	—	3.0t
		H22 H32	H22 H32	>0.20~0.50	125~165	80	4	—	0t
				>0.50~1.50			5	—	0.5t
				>1.50~3.00			6	—	1.0t
				>3.00~6.00			8	—	1.0t
		H24 H34	H24 H34	>0.20~0.50	145~185	110	3	—	0.5t
				>0.50~1.50			4	—	1.0t
				>1.50~3.00			5	—	1.0t
				>3.00~6.00			6	—	2.0t
		H26 H36	H26 H36	>0.20~0.50	165~205	135	2	—	1.0t
				>0.50~1.50			3	—	1.5t
				>1.50~3.00			4	—	2.0t
				>3.00~4.00			4	—	2.5t
		H28 H38	H28 H38	>0.20~0.50	185	160	1	—	1.5t
>0.50~1.50	2			—			2.5t		
>1.50~3.00	3			—			3.0t		
H112	H112	>6.00~12.50	115	—	8	—	—		
		>12.50~40.00	105		—	10	—		
		>40.00~80.00	100		—	16	—		
F	—	>2.50~150.00	—	—	—	—	—		

